

PRODUCT SPECIFICATIONS : Double A 75

Parameter	Methods	Values
Basis weight (g/m ²)	ISO 536	75
Thickness (µm)	ISO 534	103
Whiteness CIE	ISO 11475	165
D65 Brightness (%)	ISO 2470	111
Opacity (%)	ISO 2471	> 94
Moisture content (%)	ISO 287	4
Bendtsen roughness (ml/min)	ISO 8791-2	90
Kodak Stiffness MD (mN.m)	ISO 5629	> 0.38
Kodak Stiffness CD (mN.m)		> 0.15
Bending Stiffness MD (mN)	ISO 2493	> 100
Bending Stiffness CD (mN)		> 45

These values are indicative only.
Valid from : July 2014

TECHNICAL DATA SHEET



PRODUCT SPECIFICATIONS : DOUBLE A

Parameter	Methods	Values
Basis weight (g/m ²)	ISO 536	80
Thickness (µm)	ISO 534	107
Whiteness CIE	ISO 11475	165
D65 Brightness (%)	ISO 2470	111
Opacity (%)	ISO 2471	> 95
Moisture content (%)	ISO 287	4
Bendtsen roughness (ml/min)	ISO 8791-2	70
Kodak Stiffness MD (mN.m)	ISO 5629	> 0.40
Kodak Stiffness CD (mN.m)		> 0.16
Bending Stiffness MD (mN)	ISO 2493	> 110
Bending Stiffness CD (mN)		> 50

These values are indicative only.
Valid from : June 2014